

MYSKIM FINISH EX

MySkim Finish EX is blended with polymer modified cementitious skim coat for weathering and exterior use. To give better workability, water retentivity, bond strength. It is used as coating over on concrete and also cement rendered surfaces to provide the smooth finishing.

BENEFITS

- Good workability
- Good consistency and in handling
- Improved adhesion strength
- High durability
- Exterior

SUBSTRATE

Concrete wall
Plaster render wall
Brickwork
Blockwork

SURFACE PREPARATION

Ensure substrate is clean and sounds, remove all dust, oils, grease, coatings or traces of foreign materials. Dampen the surface before application of the plaster especially for hot and high absorbent substrates.

MIXING

Add 25kg bag of **MySkim Finish EX** to approximately 5.25 - 5.75 litres of clean water. Mix thoroughly for 3-5 minutes using mechanical mixer until the homogenous paste is achieved and lump free.

APPLICATION

1. Make sure the surface is clean. The surface can be improve with SSD condition to avoid sudden dehydration of the skim coat.
2. Spread the mixed with using the suitable trowel.
3. Use the material when is still fresh. Do not use if the adhesive start to skin and do not add extra water to re-mix it.
4. Let the coat to build the strength at least 24 hours.

TECHNICAL DATA

TECHNICAL DATA (typical values) at 23°C / 50% RH	
Appearance	Powder
Colour	Grey or White
Wet density (kg/m ³)	Approximately 1700
Dry solids content (%)	100
Mixing ratio	21 - 23% water with 25Kg powder
Adhesion strength, N/mm ²	Approximately 1.0
Thickness (mm)	3mm
Pot Life (mins)	30
Coverage	1mm : 1.5Kg/m ²

COVERAGE

approx. 1.5Kg/m², 1 mm thickness

PACKAGING

MySkim Finish EX is supplied in white and grey 25kg.

STORAGE 12 months when stored in a cool and dry place.

The data and recommendations given in this product technical data sheet is based on MyChem's current knowledge and experience. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. Therefore, user who intends to use the product must ensure beforehand that it is suitable for the application. No warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. MyChem reserve the right to change the properties of its products. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.