

MYPROOF CONCEAL WP

MyProof Conceal WP is a waterproofing membrane for conceal system with the hybrid technology.

USES FOR

Roof
Wall
Balconies
Guttering
Toilet
Kitchen

SUBSTRATE

Concrete
Screeding surface
Stone
Ceramic
Metal

SURFACE PREPARATION

The substrates must be clean, cured, mechanically strong, free of loose particles, grease, oil, paint, wax and Cement substrates must not be subject to shrinkage after tile installation. Highly porous substrates must be prime with MyMix range. Concrete must have cured at least 28 days and cementitious screeds for at least 7 days.

Cool down with water if the is too hot due to exposure to sun light to prevent extreme concrete hydration.

MIXING

Stir the MyProof Conceal WP and mix thoroughly to makesure no settlement.

APPLICATION

MyProof Conceal WP can be applied using long hair roller and brush at the rate of 0.5kg/m² per coat and wait for around 2 – 4 hours depends on the site temperature. The application shall be perpendicular to the first coat. It is require minimum of 3 coats. For areas which has a greater movement or cracks, it can be bridge using MY Mesh after first coat application of MyProof Conceal WP, then follow by second and third layers until its cover the MY Mesh.

CONSUMPTION

0.5kg /m² x 3 coats or more coats if embedded with MY Mesh.

PACKAGING

MyProof Conceal WP is supplied in 20L pail

STORAGE

24 months when stored in a cool and dry place.

TECHNICAL DATA

TECHNICAL DATA (typical values) at 23°C / 50% RH

Appearance	Paste
Colour	Dark Grey to Black
Wet density (kg/m ³)	1.25
Adhesion strength, N/mm ²	1.3 N/mm ²
Tensile Adhesion Strength, N/mm ²	App. 1.7
Elongation at break , %	App. 800
Waiting time per coat, hrs	2 – 4 (may varies due to air curing)

The data and recommendations given in this product technical data sheet is based on Mychem's current knowledge and experience. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. Therefore, user who intends to use the product must ensure beforehand that it is suitable for the application. No warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. MyChem reserve the right to change the properties of its products. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.