

MYGROUT GP

MYGROUT GP is a pumpable dual-shrinkage compensated, self-levelling, prebagged cementitious grout with extended working time to suit local ambient temperatures. Its control the shrinkage to reduce the cracks.

USES FOR

- Machine foundation
- All general purpose grouting
- Precast panels
- Grouting in column based, base infilling
- Fill core holes, rod holes and defects in concrete
- Fill in grout for hollow block walls, gaps, cavities
- Joints between precast panels and other joints
- Honeycombs (pre-packed grouting)

SURFACE PREPARATION

The substrate should be prepared by mechanical preparation techniques such as high pressure water, grit blasting etc. The substrate surface must be clean, sound and free from oil, grease, curing compound or any loose materials. All absorbent surfaces must be well saturated with clean water, but free of any surface water or puddles prior to the application of MyGrout GP.

MIXING

Add 25kg bag of **MyGrout GP** into at least 70% of clean water until paste form and add the rest of the 30% water to get the consistency needed. Mix thoroughly for 3-5 minutes using mechanical mixer until no lumps with slow speed drill at 500rpm maximum.

APPLICATION

After mixing, let the paste to settle a few seconds to release any entrapped air. The grout is then poured into the formwork. When placing grout over a large area, for sections thicker than 50 mm, it is necessary to blend with graded 10 mm silt free aggregates to minimise temperature rise generated during the curing stage. The quantity of aggregates should not exceed 1 part aggregates to 1 part MyGrout GP by weight.

PACKAGING

MyGrout GP is supplied in grey 25 kg paper bags.

STORAGE

12 months when stored in a cool and dry place.

TECHNICAL DATA

TECHNICAL DATA (typical values) at 23°C / 50% RH		
Appearance	Powder	
Colour	Grey	
Grain size	< 1.2mm	
Wet Density	Approximately 2.2kg/L	
Thickness of single pour	Minimum 5mm Maximum 50mm	
Water Ratio	4.5L – 5.0L	4.0L – 4.5L
Consistency	Pumpable	Pourable
Compressive strength, N/mm²	~ 25	~ 30
	~ 40	~ 50
	~ 55	~ 65

The data and recommendations given in this product technical data sheet is based on MyChem's current knowledge and experience. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. Therefore, user who intends to use the product must ensure beforehand that it is suitable for the application. No warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. MyChem reserve the right to change the properties of its products. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.